MATERIAL SAFETY DATA SHEET

Page 1 of 5

Sikaflex Construction Sealant (all colors)

TIANGED IN IT

1. Product And Company Identification

SIKA CORPORATION 201 Polito Ave Lyndhurst, NJ 07071 Company Contact: Kristin Kelley **Telephone Number:** (201) 933-8800

FAX Number: (201) 933-9379 Web Site: www.sikausa.com

Supplier Emergency Contacts & Phone Number

CHEMTREC: 800-424-9300 INTERNATIONAL: 703-527-3887 Manufacturer

SIKA CORPORATION 201 Polito Ave Lyndhurst, NJ 07071

Company Contact: Kristin Kelley **Telephone Number:** (201) 933-8800 FAX Number: (201) 933-9379

Web Site: www.sikausa.com

Manufacturer Emergency Contacts & Phone Number

CHEMTREC: 800-424-9300 INTERNATIONAL: 703-527-3887

Issue Date: 12/27/2002

Product Name: Sikaflex Construction Sealant (all colors)

CAS Number: Not Established Chemical Family: POLYURETHANE Chemical Formula: RMF-2380

MSDS Number: 2610 Product Code: 0437-54

2.	Composition/	/Information	On	Ingredients
----	--------------	--------------	----	-------------

Ingredient Name	CAS Number		Percent Of Total Weight			
POLYISOCYANATE PREPOLYMER	TradeSecret					
XYLENE (MIXED ISOMERS)		٧	4			

3. Hazards Identification

Eye Hazards

May cause eye irritation.

Skin Hazards

May cause skin irritation. May cause skin sensitization.

Ingestion Hazards

May be harmful if swallowed.

3. Hazards Identification - Continued

Ingestion Hazards - Continued

Inhalation Hazards

May cause nose, throat, and lung irritation. May cause respiratory tract irritation.

4. First Aid Measures

Eye

In case of contact, immediately flush eyes with plenty of water. Get medical attention immediately if irritation develops and persists.

Skin

In case of contact, immediately flush skin with soap and plenty of water. Get medical attention immediately if irritation (redness, rash, blistering) develops and persists.

Ingestion

If swallowed, do not induce vomiting unless directed to do so by medical personnel.

Inhalation

Remove to fresh air. If not breathing, give artificial respiration.

5. Fire Fighting Measures

Flash Point Method: ASTM D4359

Fire And Explosion Hazards

DURING A FIRE, IRRITATING AND/OR TOXIC GASES AND AEROSOLS FROM THE DECOMPOSITION/COMBUSTION PRODUCTS MAY BE PRESENT.

Extinguishing Media

In case of fire, use water spray (fog) foam, dry chemical, or CO2.

Fire Fighting Instructions

Firefighters should wear self-contained breathing apparatus and full protective gear.

6. Accidental Release Measures

Avoid release to the environment. Use appropriate personal protective equipment (PPE). Contain spill and collect with absorbent material and transfer into suitable containers. Ventilate enclosed area.

7. Handling And Storage

Handling And Storage Precautions

STORE AT 40-95F. CONDITION TO 65-85F BEFORE USING. IF CLOSED CONTAINER IS EXPOSED TO HEAT, PRESSURE CAN BUILD UP. IF MOISTURE ENTERS CONTAINER, PRESSUREMAY BUILD UP DUE TO REACTION. STORE IN COOL DRY AREA IN TIGHTLY CLOSED CONT AINERS, AWAY FROM SPARKS AND OPEN FLAMES.

Work/Hygienic Practices

Wash thoroughly with soap and water after handling.

8. Exposure Controls/Personal Protection

Engineering Controls

Use with adequate general and local exhaust ventilation.

Eye/Face Protection

Safety glasses with side shields or goggles.

Skin Protection

Chemical-resistant gloves. Lab coat or other work clothing. Launder before reuse.

Respiratory Protection

In areas where the P.E.L.s are exceeded, use a properly fitted NIOSH-approved respirator.

Other/General Protection

WASH THOROUGHLY AFTER HANDLING.

Ingredient(s) - Exposure Limits

XYLENE (MIXED ISOMERS) ACGIH TLV-STEL 150 ppm ACGIH TLV-TWA 100 ppm OSHA PEL-TWA 100 ppm

9. Physical And Chemical Properties

<u>Appearance</u>

PASTE (solid) IN ALL COLORS

<u>Odor</u>

AROMATIC ODOR

Chemical Type: Mixture Physical State: Solid Melting Point: N/AV °F Boiling Point: N/AV °F Specific Gravity: 1.39 Percent Volatiles: <4% Percent VOCs: <4%

Packing Density: 11.59#/GAL Vapor Pressure: N/AV Vapor Density: > AIR

Solubility: N/AV

Evaporation Rate: SLOWER THAN ETHER

10. Stability And Reactivity

Stability: STABLE

Hazardous Polymerization: WILL NOT OCCUR

Conditions To Avoid (Stability)

OPEN FLAME, HEAT

Incompatible Materials

WATER, ALCOHOLS AND AMINES

10. Stability And Reactivity - Continued

Hazardous Decomposition Products

CO, CO2, NOx, SMOKE, FUMES

11. Toxicological Information

No Data Available...

12. Ecological Information

No Data Available...

13. Disposal Considerations

Dispose in accordance with applicable federal, state and local government regulations.

14. Transport Information

Proper Shipping Name

NOT REGULATED PER D.O.T.

15. Regulatory Information

U.S. Regulatory Information

All ingredients of this product are listed or are excluded from listing under the U.S. Toxic Substances Control Act (TSCA) Chemical Substance Inventory.

SARA Hazard Classes

Acute Health Hazard Chronic Health Hazard

SARA Section 313 Notification

This product contains the following toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-To-Know Act of 1986 and of 40 CFR 372. This information must be included in all MSDSs that are copied and distributed for this material.

Ingredient(s) - U.S. Regulatory Information

XYLENE (MIXED ISOMERS)

SARA Title III - Section 313 Form "R"/TRI Reportable Chemical

SARA - Acute Health Hazard SARA - Chronic Health Hazard

SARA - Fire Hazard

Ingredient(s) - State Regulations

XYLENE (MIXED ISOMERS)

New Jersey - Workplace Hazard New Jersey - Environmental Hazard

New Jersey - Special Hazard

Pennsylvania - Workplace Hazard

Pennsylvania - Environmental Hazard

Massachusetts - Hazardous Substance

New York City - Hazardous Substance

16. Other Information

HMIS Rating

Health: 2 Fire: 1 Reactivity: 0

16. Other Information - Continued

HMIS Rating - Continued

PPE: C

Revision/Preparer Information MSDS Preparer: Kristin Kelley

This MSDS Supercedes A Previous MSDS Dated: 04/18/2001

Disclaimer

The data in this Material Safety Data Sheet relates only to the specific material herein and does not relate to use in combination with any other material or in any process. The information set forth herein is based on technical data that Sika believes to be reliable as of the date hereof. Since conditions of use are outside our control, we make no warranties, express or implied andassume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

SIKA CORPORATION

Printed Using MSDS Generator™ 2000